

Intercure 99

Increase your productivity

As a single coat polyaspartic primer finish, Intercure® 99 can replace two coat systems for ISO 12944 C3 environments.

Drying hard in 1½ hours at 25°C (77°F), Intercure® 99 can increase productivity, reduce VOC levels and provide anti-corrosive protection with long lasting aesthetics.

- High solids polyaspartic
- Single coat direct to metal application for ISO 12944 C3 environments
- Satisfies ISO 12944 C4 and C5 environments with a suitable primer
- Rapid cure maximizes fabrication throughput
- Fast forming abrasion resistance enables early handling and minimizes damages
- Available in a wide range of colors via the Chromascan® mixing scheme
- Excellent long term aesthetic performance
- Low temperature cure down to 5°C (41°F)
- HAPS free formulation

Polyaspartic technology

Intercure® 99 is a premium direct-to-metal coating from International®. Based on polyaspartic technology, Intercure® 99 offers fast drying even at low temperatures to help increase productivity and throughput.

Simple specification


Whatever the environment, Intercure® 99 can meet requirements simply and effectively by eliminating one complete coat:

- In moderately corrosive conditions up to ISO 12944 C3, a single coat of Intercure® 99 can be applied direct to a variety of substrates.
- For more corrosive environments such as C4 and C5, Intercure® 99 can be applied over a suitable primer to provide long term corrosion protection.
- In both scenarios, Intercure® 99 allows the coated structure to be moved or returned to service much faster than with traditional multicoat systems.

Complexity reduction

Intercure® 99 is not the only polyaspartic coating available from International, we also offer a semi-gloss version in the form of Intercure® 4500. Both products now share the same mix ratio (4:1 by volume) and curing agent, so can be interchanged more easily.

Faster handling



Technical information

Color	Wide range via Chromascan® system		
Volume solids	80% ±3%		
Film thickness	150 - 250 microns (6 - 10 mils)		
Mix ratio	4:1 by volume		
Temperature	Touch Dry	Hard Dry*	Min. Recoat*
5°C (41°F)	1½ hours	4 hours	4 hours
15°C (59°F)	1 hour	3 hours	3 hours
25°C (77°F)	½ hour	1½ hours	1½ hours
40°C (104°F)	½ hour	1½ hours	1½ hours
VOC's	1.83 lb/gal (220g/l) EPA method 24 165 g/kg EU Solvent Emissions Directive (Council Directive 1999/13/EC)		

* Dry times will be significantly faster in high humidity conditions

Test data

	TEST METHOD	SPECIFICATION DETAILS	RESULTS
Anti-corrosive	ISO 12944 C3 comprising 480 hours Hot Salt Spray 240 hours Condensation @ 35°C (95°F)	1 x 175 microns (7mils) dft. ISO 8501 Sa2½ or SSPC-SP6 blasted substrate	No blistering and less than 1mm creep from the scribe on completion of the test
Adhesion	ISO 4624	1 x 175 microns (7mils) dft. ISO 8501 Sa2½ or SSPC-SP6 blasted substrate	Typically greater than 12MPa (1,740 PSI)
Impact	ASTM D2794	1 x 175 microns (7mils) dft. ISO 8501 Sa2½ or SSPC-SP6 blasted substrate	Typically no disbondment following a 6 joule direct impact
Gloss retention	ISO 11507	1 x 175 microns (7mils) dft. ISO 8501 Sa2½ or SSPC-SP6 blasted substrate	>60% retention after 1,500hrs QUV-A exposure
Abrasion resistance	ASTM D4060	1 x 175 microns (7mils) Intercure® 99 applied directly over abraded steel plate	Average 102mg weight loss per 1,000 cycles using CS10 wheels and a 1kg loading
Flexibility	ASTM D522	1 x 175 microns (7mils) dft. ISO 8501 Sa2½ or SSPC-SP6 blasted substrate	No cracking at 5mm mandrel diameter

www.international-pc.com
pc.communication@akzonobel.com

All trademarks mentioned in this publication are owned by the AkzoNobel group of companies. © Akzo Nobel 2014.
AkzoNobel has used its best endeavors to ensure that the information contained in this publication is correct at the time of printing.
Please contact your local representative if you have any questions.
Unless otherwise agreed by us in writing, any contract to purchase products referred to in this brochure and any advice which we give in connection with the supply of products are subject to our standard conditions of sale.