



TECHNICAL DATASHEET

8-110 / 8-111

2K WB SINGLE STAGE TOPCOAT / FAST CURING SYSTEM

PRODUCT DESCRIPTION

8-110 (Gloss) and 8-111 (Matt) are a two component, waterborne, polyurethane, single stage topcoat, suitable for direct application to properly prepared steel, galvanized steel, phosphated steel or aluminium surfaces exposed to weathering, mechanical and chemical stress, for both interior and exterior use.

It provides from high gloss to matt finish, colour retention and excellent hardness.

It is especially recommended for high quality finishes in industrial agricultural equipment and machinery.

8-11x when activated with 9-125 Fast Curing Hardener provides a short flash-off between coats and prior baking in a short time. It is also air dry capable.

SELECTION AND PREPARATION OF SUBSTRATES



Substrate

Bare Steel
Phosphated Steel
Galvanised Steel
Light Alloys
Aluminium

Sand

P80 – 120 (dry)
Scotchbrite
Scotchbrite
P280 – 320 (dry)
P280 – 320 (dry)


Degrease

All surfaces should be thoroughly degreased using the appropriate cleaner both before and after preparation.

VERY IMPORTANT: Degrease **thoroughly** prior to painting. All substrates should be free from any contamination such as oil, grease and rust.

GLOSS CHART GUIDE


GLOSS CHART GUIDE		
		All colours
High Gloss	Tinting Ratio (By weight):	Binder 8-110: 60 WB Tinters: 40
Semi-Gloss (70%)	Tinting Ratio (By weight):	Binder 8-111/8-110: 36/24 WB Tinters: 40
Semi-Matt (30%)	Tinting Ratio (By weight)	Binder 8-111/8-110: 48/12 WB Tinters: 40
Matt (15-20%)	Tinting Ratio (By weight):	Binder 8-111: 60 WB Tinters: 40



Mixing ratio (by weight):

Mixing ratio (by volume):

Pot life 20°C:



Spray viscosity:

Spray gun set up:

Spray pressure:




Number of coats:

Flash off between coats:



Flash off before stoving:



Spray viscosity:


Spray gun set up:

Spray pressure:



Number of coats:

Flash off between coats:



Flash off before stoving:

Topcoat 8-110 / 8-111 1000

Hardener 9-125 (*) 400

Mix thoroughly and then add:

15 – 30% Water – Conventional application

Topcoat 8-110 / 8-111 2,5

Hardener 9-125 (*) 1

Mix thoroughly and then add:-

15 – 30% Water – Conventional application

(*) It is very important to thoroughly mix topcoat and hardener during 5 minutes before adding water

2 hours

Conventional 1 Visit Application

65-70 sec DIN 4 at 20°C

1.6 – 1.8 mm

2 – 3 bar

1 light coat, 2 minute flash off, 1 normal coat

2 minutes at 20°C

20 minutes at 20°C

Conventional 2 Coats Application

55-60 sec DIN 4 at 20°C

1.6 – 1.8 mm

2 – 3 bar

1 light coat, 15 - 30 minutes flash off, 1 normal coat

15-20 minutes at 20°C, until surface dry

20 minutes at 20°C

Air Assisted Airless Application

NOT RECOMMENDED

APPLICATION GUIDE



Drying times at 60°C (metalT°):

30 minutes (for 60-80 µm DFT)

Drying times at 20°C

10-15 minutes

Dust free:

2 - 3 hours

Touch free:

6 hours

Handling:

8-9 hours

Through Dry:

Overnight

Recommended thickness:

140 microns max. – wet film thickness
60 – 80 microns – dry film thickness

Recoat time:

min. 8 hours and max. 24 hours at 20°C
without flatting

The drying times quoted are approximate times and will vary depending on drying conditions and film thickness. Poor ventilation, temperatures below 20°C, above 85% RH and excessive film thickness will extend the drying times.

APPLICATION GUIDE – BRUSH / ROLLER APPLICATION

Equipment type advised : short haired mohair roller or solvent resistant brush

		Volume	Weight
Mixing ratio:	Mixed colour	3 vol	1000
	9-110	1 vol	300
	Water	0.3 vol	100-150

Application in 2 medium coats, leave a minimum 45 minutes drying time between coats.

TECHNICAL DATA RFU

	8-110	8-111
Theoretical coverage:	5.2 – 6.4	5.3 – 5.5 m ² /L of paint ready to use for 70µm of thickness
Solid content (by vol):	39 - 50%	40 – 42%
Solid content (by w):	43 - 59%	44 – 46%
% solvent:	9 – 10%	7 – 9%
Density:	1040 – 1190	1050 – 1180 g/L

Storage:

STORE FREE FROM FROST ABOVE 5°C

Prolonged exposure to high temperatures or direct sources of heat should be avoided.

HEALTH AND SAFETY

These products are for professional painting only, and are not to be used for purposes other than those specified. The information on this TDS is based on present scientific and technical knowledge, and it is the responsibility of the user to take all necessary steps in order to ensure the suitability of the product for the intended purpose. For Health and Safety information please refer to the material Safety Data Sheet, also available at:

<http://corporateportal.ppg.com/Refinish/Selemix>

For further information please contact:

Customer Service Sales Group
PPG Industries (UK) Ltd
Needham Road
Stowmarket
Suffolk IP14 2AD

Tel: 01449 771771

Fax: 01449 773472

