Technical Data Sheet Product number 0641







Funcosil SNL Odourless

Clear, hydrophobising impregnation on a silane/siloxane base with odourless solvents

	Availability				
	Quantity per pallet	84	24	2	1
	Packaging unit	5 l	30 l	200 l*	1000 l*
	Type of container	Tin canister	Tin canister	Drum	Container
	Container code	05	30	69	61
	Art. no.				
	0641				
*on request					

Application rate	Brick masonry work, fine-pored: min. 0.8 l/m ² Brick masonry work, coarse-pored: min. 1.0 l/m ² Sand-lime brick, smooth: min. 0.5 l/m ² Sand-lime brick, cleft, bossed: min. 0.7 l/m ² Render: min. 0.5 l/m ² Aerated concrete: min. 1.0 l/m ² Fibre-reinforced cement: min. 0.3 l/m ² Concrete modular block: min. 1.2 l/m ² Natural stone, fine-pored: min. 0.6 l/m ² Natural stone, coarse-pored: min. 1.5 l/m ² Apply to a large enough trial surface (1-2 m ²) to determine the precise amount of impregnation agent required.
Range of use	 Protection of facades against driving rain Reduces susceptibility to dirt and green discolouration Subsequent treatment/renewal of hydrophobic surfaces Subsequent impregnation of mineral paint coatings Porous, mineral building materials such as brick masonry work, sandstone/sand-lime brick, mineral renders and aerated concrete
Property profile	 Improves resistance to frost and de-icing salts Highly water-repellent Enables water vapour diffusion Outstanding penetration UV-resistant Alkali-resistant Excellent long-term effect Odorless Reduces energy loss





Characteristic data of the product	Carrier material	dearomatised hydrocarbons		
product	Density (20 °C)	approx. 0.78		
	Runout time s in DIN 4 cup	approx. 11		
	Active ingredient	silane/siloxane		
	Active ingredient content, % by mass Flash point °C Odour	approx. 7		
		> 61		
		neutral		
	Appearance	clear, liquid		
	The values stated represent typical characteristic data of the product and are not to be understood as bindi product specifications.			
Certificates	> TU Hamburg report, long-term weathering			
Possible system products	 > BFA* (0673) *Use biocidal products carefully. Always read the label and product information before use. 			
Preparation	 Substrate requirements The substrate must be clean, dust-free and dry. Substrate preparation Any construction defects such as cracks, cracked joints, defective connections, rising damp and hygroscopic moisture must be remedied in advance. Perform any necessary cleaning gently, e.g. by spraying with cold or warm water or by steam-cleaning; use the rotec Soft Whirl Jet 25 l (5235) or Remmers cleaning products (e.g. Traffic Film Remover (0671), Clean FP (0666), Clean AC (0672), Combi WR (0675)) on tough stains. 			
Directions	Conditions for use			
≤ +25 °C ≥ +10 °C	Temperature of the material, air and substrate: from min. +10 °C to max. +25 °C Apply the primer abundantly by flow coating without pressure (avoid misting), so that - 50 cm long liquid film flows down the surface. Apply on one section at a time, moving from top to bottom, and immediately go over v a large brush. Repeat the application several (at least two) times (wet on damp) until no further mat is absorbed by the substrate. On surfaces where a spraying application is not possible, apply by brush or roller mak sure the tools are always well saturated.			
Tips on use	Take appropriate measures to protect adjacent building elements and materials that should not come into contact with the product. Protect freshly treated surfaces from driving rain, wind, sunlight and condensation. Remove any excess impregnation agent within 1 hour using V 101 thinner.			
Notes	Deviations from applicable regulations must be agreed separately. The relevant test certificates must be observed when planning and carrying out work. Water must not be allowed to penetrate behind the hydrophobized zone. Not suitable for materials that are sensitive to solvents, such as polystyrene or bitumen			

Remmers (UK) Ltd 🔳 Unit B1 · The Fleming Centre · Fleming Way Crawley · West Sussex · RH10 9NN 🔳 Tel: 01293 594010 📕 Fax: 01293 594037 🛢 sales@remmers.co.uk 🔳 www.remmers.co.uk 0641 TM-2-205 10/19 EW_AMy_JEn 2/3

Funcosil SNL Odourless	Funcosi	l SNL	Odour	less
------------------------	---------	-------	-------	------

Technical Data Sheet Product number 0641





	The level of absorption is crucial for the impregnation agent to work at its best. This depends on the respective pore volume and moisture content of the building material. Carry out a quantitative analysis of aggressive salts if there are any salts present that could damage building materials. High concentrations of harmful salts can cause major structural damage that impregnation cannot prevent. Testing effectiveness: The water absorption of mineral building materials can be determined using the Funcosil Test Plate or the Funcosil Test Tube developed by Professor Karsten (Funcosil Facade Testing Kit, article no. 4954). Testing can only be carried out at the earliest 6 weeks after application. A test of effectiveness needs to be carried out on carbonaceous natural stone. Always set up a trial area/trial areas first.
Tools / Cleaning	Solvent-resistant low-pressure conveying and spraying equipment, liquid pumps, brush, surface brush and lamb's wool roller
	Tools must be clean and dry. After use and before prolonged interruptions of work clean tools with Thinner V 101.
Storage / Shelf life	If stored unopened in its original container in a cool, dry place and protected against frost, the product will keep for at least 24 months. Use the contents of open containers as quickly as possible.
Safety data / Regulations	For further information on the safety aspects of transporting, storing and handling the product and on disposal and environmental matters, please see the current Safety Data Sheet.
Personal protective equipment	Respiratory protection with a particle filter P2 must be worn during spraying, together with protective goggles. Wear suitable protective gloves and clothing.
Disposal	Dispose of contents/container in accordance with local/regional/national/international regulations.

Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.