

A pump-applied floor screed designed for application at a thickness of between 2 – 30 mm.

weberfloor 4150 fine flow



About this product

weberfloor 4150 fine flow is a pump-applied floor screed formulated from special cements, aggregates, supplementary binders and chemical admixtures. It is supplied as a pre-blended dry powder designed for application at a thickness of between 2 – 30 mm. The product is casein free.

weberfloor 4150 fine flow is designed for levelling of floors in apartments, offices and public buildings where the requirement for surface tensile strength is $>1.0 \text{ N/mm}^2$. The levelled floor can be covered with ceramics, terrazzo, PVC, linoleum etc.

Technical data

Application temperature	+10°C to +25°C optimal +15°C to +20°C
Maximum thickness	30 mm
Minimum thickness	2 mm
Recommended layer thickness	6 – 10 mm
Water demand	5 litres/25 kg (20 %)
Adhesion strength (28 day)	$>1.0 \text{ N/mm}^2$
Compressive strength class	C 25
Flexural strength class	F 6
Tensile strength	$>1.5 \text{ N/mm}^2$
Shrinkage (28 days)	$< 0.04 \text{ mm/m}$
Flow rate according to (Weber standard)	240 – 255 mm
Hardening time (before foot traffic)	2 – 4 hours
Hardening time (before common traffic)	Final floor covering after 1 – 3 weeks depending on the layer thickness and drying conditions.
Pot life	20 min (after adding water)
Wear resistance (RWA Class)	RWFC 350 (thickness 2 – 30 mm)
Material consumption	1.7 kg/m ² /mm

Uses

For levelling:

- Concrete
- Lightweight concrete

Suitable for covering with:

- Tiling
- Carpeting
- Flexible floor coverings
- Parquet flooring

Constraints

Not to be used where some movement is expected (e.g. underfloor heating).

Do not use:

- on permanently damp floors or floors with rising damp;
- on friable or unstable floors;
- in industrial areas;
- on exterior floors.

Features and benefits

- ▲ Manufactured under a BSI Quality Assurance Scheme ISO 9001
- ▲ Excellent spreading and smoothing characteristics
- ▲ Low alkalinity
- ▲ Casein-free
- ▲ Low emissions

weberfloor 4150 fine flow

Preparation

Substrate

Suitable substrates are concrete and lightweight-concrete. The surface strength of the substrate must be greater than 1N/mm².

Preparation and priming

The substrate should be clean, free from dust, grease and other impurities that might prevent adhesion. Holes and leaks in the substrate should be sealed. Floor drains etc. should be protected and large irregularities (>30 mm) should be filled. The infill should be left to set before the next application.

The substrate should be vacuum cleaned, prepared and primed with **weberfloor 4716 primer** according to the instructions on the data sheet. Priming improves the screed's adhesion to the substrate and prevents the formation of air bubbles and de-watering of the screed. Priming also improves the flow properties of the screed. Dry and very porous substrates (cast-in-situ concrete floors) may need to be treated twice. If the screed is applied in more than one layer, each layer must be primed.

Mixing

weberfloor 4150 fine flow is mixed with clean water using an automatic screed mixer approved by **Weber**. For manual mixing the screed should be mixed with a suitable paddle mixer for at least 2 minutes.

The suitable water amount is 20% (of the powder's dry weight), which corresponds to 5 litres/25 kg bag. Pot-life is 20 min. from mixing with water. The temperature of the screed must be at least +10°C. The flow properties of the screed should be checked by using a **weberfloor 4931 flow ring and plate** before and regularly during pumping. Excess water causes separation and weakens the strength of the screed surface.

Application

Light ventilation in the working area is necessary but windows and door openings must be closed sufficiently to avoid draughts during and for 3 days after application. During application, and for at least 1 week afterwards, the substrate and ambient temperature should not fall below +10°C or rise above +25°C. The relative humidity of the substrate must be <95%.

To achieve the best finish, the floor area should be divided into bays of 6 to 8 metres depending on pump capacity and application thickness. **weberfloor 4965 barrier foam** should be used to form bays and stop ends. Pumping is carried out in sections so that a new section is pumped as quickly as possible and to maintain a wet edge. A wide spatula or spike roller should be used to assist the self-levelling process.

Overlay

weberfloor 4150 fine flow is compatible with most common floor finishes and adhesives.

weberfloor 4150 fine flow should not be painted or used without a floor finish.

Drying time

The screed can receive foot traffic after a drying time of 2 – 4 hours at an ambient temperature of +20°C. If necessary, the surface can be ground after 2 days following application. Floor covering can be installed after 1 – 3 weeks depending on layer thickness and drying conditions.

High humidity of the substrate and poor drying conditions prolong the setting time.

Packaging

weberfloor 4150 fine flow is packed in 25 kg polythene-lined paper sacks.

Storage and shelf life

When stored unopened in a cool, dry place at temperatures above 5°C, shelf life is 12 months from date of manufacture.

Poor storage conditions may have an adverse impact on the levelling properties.

Health and safety

Contains cement (Contains chromium (VI). May produce an allergic reaction). Harmful by inhalation. Irritating to eyes and skin. Keep out of the reach of children. In case of contact with eyes, rinse immediately with plenty of water and seek medical help. After contact with skin, wash immediately with plenty of soap and water. Wear suitable protective clothing, gloves and eye/face protection.

For further information, please request the Material Safety Data Sheet for this product.

Technical services

Weber's Customer Services Department has a team of experienced advisors available to provide on-site advice both at the specification stage and during application. Detailed specifications can be provided for specific projects or more general works. Site visits and on-site demonstrations can be arranged on request.

Technical helpline

Tel: 08703 330 070
e-mail: technical@netweber.co.uk

Sales enquiries

Weber products are distributed throughout the UK through selected stockists and distributors. Please contact the relevant Customer Services Team below for all product orders and enquiries.

UK and Ireland

Tel: 08703 330 070
Fax: 0800 014 2995
e-mail: customerservice@netweber.co.uk

Saint-Gobain Weber

Dickens House, Enterprise Way, Maulden Road, Flitwick, Bedford MK45 5BY, UK
Tel: 08703 330 070 Fax: 0800 014 2995 e-mail: mail@netweber.co.uk
www.netweber.co.uk

To the best of our knowledge and belief, this information is true and accurate, but as conditions of use and any labour involved are beyond our control, the end user must satisfy himself by prior testing that the product is suitable for his specific application, and no responsibility can be accepted, or any warranty given by our Representatives, Agents or Distributors. Products are sold subject to our Standard Conditions of Sale and the end user should ensure that he has consulted our latest literature.