

*Polymer-modified cementitious
binder for repair mortars*

webercem bondcoat



About this product

webercem bondcoat is a single-component polymer-modified, cementitious bonding aid. It requires only the addition of clean water to produce a bonding slurry for **webercem HB30**, **webercem HB40** and **webercem lightweight** mortars.

This product has been formulated to comply with the requirements of BS EN 1504-3 for a bonding primer.

Technical data

Mixed density	1.67 kg/litre
Typical coating thickness	1 – 2 mm
Pot life	20 – 30 minutes at 20°C

Uses

- Holding primer for the following repair materials:
webercem HB30
webercem HB40
webercem lightweight
- Improved bond of cementitious repair mortars to concrete

Features and benefits

- ▲ High initial grab to improve the build of the repair mortar and promote the bond to the concrete
- ▲ This product has been formulated to comply with the requirements of BS EN 1504-3
- ▲ Contains fibres for improved thixotropy
- ▲ Cementitious, contains no solvents
- ▲ Single-component; simply mix with water

EU VOC regulations 2008

EU limit for webercem bondcoat (cat A/g or j): g-50 g/l, j-140 g/l (2007)/g-50 g/l, j-140 g/l (2010). **webercem bondcoat** contains <1 g/l VOC.

webercem bondcoat

Preparation

Surfaces must be clean and free from laitance, mould release, oil and other surface coatings.

Thoroughly soak the concrete and remove all surface water prior to application.

Concrete substrates

Concrete substrates must be adequately prepared either by use of a suitable mechanical method such as water blasting, needle gunning, or by such other means as appropriate to give a clean, freshly exposed surface.

Old concrete surfaces contaminated with oil or grease require suitable preparation such as steam cleaning in conjunction with a suitable detergent. Care must be taken to ensure that the oil or grease is removed from the surface and not simply spread over a larger area.

New concrete should be at least 14 days old.

Steel substrates

Steel substrates should be cleaned by a grit blasting treatment to Swedish Standard Specification SA 2½ (equivalent to BS 7079-A1) immediately prior to bonding. However, in many instances where corrosion is absent, wire brushing to obtain a clean surface may be adequate.

Where exposed reinforcement is contaminated with chloride or other material which may cause corrosion, the whole of the circumference of the contaminated reinforcement shall be cleaned in accordance with BS EN 1504-10 Clause 7.3.2 (e).

Mixing

Use a forced action mixer or a MR4-120B paddle with a high powered low speed drill. Mix 20 kg of **webercem bondcoat** with 8 litres of clean water by adding the **webercem bondcoat** powder to water and stirring continuously to a brushable slurry consistency.

For small quantities mix 2½ parts **webercem bondcoat** with 1 part clean water by volume. Use a palette knife or a rigid flat stick and mix to a creamy consistency. The ideal mix should allow a stipple finish.

If the mix stiffens too quickly, it can be remixed easily with no more water. **Extra water should not be added.**

Application

To steel reinforcement

Using a stiff bristle brush, apply one full unbroken coat of **webercem bondcoat** to the steel, ensuring that the backs of the reinforcing bars are fully coated with at least a 2 mm thickness of the **webercem bondcoat**.

webercem bondcoat can be used as a holding primer for steel. Apply a 2-coat application to ensure a pinhole-free coating, making sure that the back of the steel bars are fully coated. The holding primer can be left for up to 3 days before reapplying the bondcoat to the protected coated steel bars and the substrate and before applying the repair mortar. Stipple finish the applied slurry coat.

To damp concrete substrate

Apply **webercem bondcoat** to an area that can be overlaid with the appropriate HB mortar within 20 minutes.

Apply immediately after mixing to the prepared concrete surface.

Use a stiff brush to scrub the slurry well into the surface. Stipple finish the applied slurry coat. Overcoat the steel if it has been used as a holding primer.

Place the mortar onto the slurry while it is tacky. In hot weather the slurry will dry quickly once it is applied (ie within 15 minutes) and it is prudent to mix the mortar first ready for application.

If the **webercem bondcoat** primer has hardened before the mortar has been applied, it must be removed otherwise it will create a debonding layer.

It must be removed mechanically and **webercem bondcoat** re-applied.

Packaging

webercem bondcoat is supplied in 20 kg bags.

Coverage and yield

20 kg will cover approximately 5 to 8 m² depending on surface profile/texture.

Yield is approx. 16.5 litres.

Storage and shelf life

Shelf life is 12 months from date of manufacture if stored properly in unopened and undamaged packaging in dry conditions within the temperature range 5°C to 25°C. If stored at higher temperatures and high humidity, the shelf life will be reduced. Use within 3 days once the bags are opened.

Protect from frost.

Health and safety

Contains cement (Contains chromium (VI). May produce an allergic reaction). Harmful by inhalation. Irritating to eyes and skin. Keep out of the reach of children. In case of contact with eyes, rinse immediately with plenty of water and seek medical help. After contact with skin, wash immediately with plenty of soap and water. Wear suitable protective clothing, gloves and eye/face protection.

For further information, please request the Material Safety Data Sheet for this product.

Technical services

Weber's Customer Services Department has a team of experienced advisors available to provide on-site advice both at the specification stage and during application. Detailed specifications can be provided for specific projects or more general works. Site visits and on-site demonstrations can be arranged on request.

Technical helpline

Tel: 08703 330 070
e-mail: technical@netweber.co.uk

Sales enquiries

Weber products are distributed throughout the UK through selected stockists and distributors. Please contact the relevant Customer Services Team below for all product orders and enquiries.

UK and Ireland

Tel: 08703 330 070
Fax: 0800 014 2995
e-mail: sales@netweber.co.uk

Saint-Gobain Weber

Dickens House, Enterprise Way, Maulden Road, Flitwick, Bedford MK45 5BY, UK
Tel: 08703 330 070 Fax: 0800 014 2995 e-mail: mail@netweber.co.uk
www.netweber.co.uk

To the best of our knowledge and belief, this information is true and accurate, but as conditions of use and any labour involved are beyond our control, the end user must satisfy himself by prior testing that the product is suitable for his specific application, and no responsibility can be accepted, or any warranty given by our Representatives, Agents or Distributors. Products are sold subject to our Standard Conditions of Sale and the end user should ensure that he has consulted our latest literature.