



Low Temperature Plasticiser

ADOFLOW WINTERAID is a chloride-free accelerating admixture with plasticising properties. It is ideal for use when low temperatures require an accelerated set and strength gain of the mortar or concrete.

Advantages

- · Accelerate initial and final set
- Provide higher early strengths
- Increase rate of strength gain
- Permit earlier release of formwork

- Provide safer winter concreting without delays
- Improve workability
- Enable reduction in water content.

Application

1250 ml. ADOFLOW WINTERAID to 50Kg Portland Cement added preferably to the gauging water or alternatively add direct into the mixer at the same time as the gauging water after the aggregates and cement have been mixed.

Accidental overdosing, even to double the recommended quantity, will result in slight increase in initial acceleration but no significant alteration in cured properties.

ADOFLOW WINTERAID is suitable for use with all types of Portland Cements. It is possible that on prolonged storage at very low temperatures a slight sediment may occur in the material. An occasional stir will quickly revert the sediment back into solution. Ensure all materials used are free from ice and the temperature of the mix prior to placing is not below 4°C.

Typical Effect on Compressive Strengths at Different Ages

Tests carried out to compare a concrete mix including ADOFLOW WINTERAID with a control mix. The aggregate/cement ratio of the mixes 4.7:1,water/cement ratio adjusted to give equal slump of 65mm, and curing temperature was 15°C. The results obtained are typically as follows:

ADOFLOW WINTERAID	Type of	W/C		Compressi	Compressive Strength (Mpa.)			
Per 50kg cement	Cement	Ratio	16 hrs	24 hrs	3 days	7 days	28 days	
Nil	OPC	0.58	4.9	8.3	16.2	26.5	41.8	
1250 ml	OPC	0.54	12.9	15.5	34.2	42.1	49.2	

Typically tests show that the percentage early strength gain over a control mix is greater when the cement content of the mix is greater.

Storage

Store in cool temperature, but above freezing, and stir just prior to use. In the event of freezing, material should be completely thawed and then thoroughly mixed before use.

Shelf Life

If stored in accordance to the above, In these circumstances shelf life is approximately 1 year from date of manufacture.

Date of issue 03.07.2014 Tech Data Sheet no. 358 Revision no. v2 Page 1 of 2



Specification

ADOFLOW WINTERAID is manufactured by Adomast Manufacturing Ltd and shall be applied in accordance with the manufacturer's instructions

Health and Safety

ADOFLOW WINTERAID is non-hazardous in normal use. If splashes should affect the eyes bathe immediately with copious quantities of clean water and then immediately seek medical advice.

See separate Safety Data Sheet for further details

Date of issue 03.07.2014 Tech Data Sheet no. 358 Revision no. v2 Page 2 of 2