

EXTERNAL SCREEN CLASSIC 5500 MÉTAL





www.mermet.co.uk 01989 750910 info@mermet.co.uk

COLLECTION

2021

THE FIRST METALISED SCREEN FABRIC FOR EXTERNAL AND INTERNAL APPLICATION

MAXIMUM HEAT PROTECTION AND VISUAL COMFORT

285 CM LARGE WIDTH


- EXCELLENT HEAT PROTECTION: up to 98% OF SOLAR RADIATION REFLECTED by external blinds (gtot = 0,02 / glazing g = 0,32 and U = 1,1), comfort classification 4 (very good effect) according to EN 14501 standard
- EXCELLENT GLARE CONTROL: up to 97% OF LIGHT RAYS FILTERED (Tv = 3%), comfort classification 3 (good effect) according to EN 14501 standard
- CONSISTENT AESTHETIC: coordinates with the BUILDING FACADE thanks to the perfect integration of the metallic side with the building construction
- VERY GOOD TRANSPARENCY for excellent vision to the outside
- Perfect match with side channels systems such as ZIP
- WEATHER-RESISTANT and UV fading resistant
- DIMENSIONAL STABILITY, DURABILITY (test of 10.000 cycles, class 3 NF EN 13561), MECHANICAL RESISTANCE: perfect flatness even in large dimensions
- Health & Safety: conforms to standard requirements for buildings open to the public

TECHNICAL DATA

5500 MÉTAL					
Composition	42% Fibreglass - 58% PVC				
Fire, smoke classification and other official test reports	M1 (F) - NFP 92 503 BS (GB) - 476 Pt 6 & 7 Class 0 B1 (DE) - DIN 4102-1 FR (US) - NFPA 701 Euroclass C-s3-d0 (EU) - EN 13501-1 HHV: 13,3 MJ/kg (6,92 MJ/m²) mounted according to EN 13823 & EN 14716 HHV: 13,3 MJ/kg (6,92 MJ/m²)				
Health, safety	Greenguard [®] : Guarantee of indoor air quality (VOC) Antibacterial: More than 99% of bacteria destroyed - ASTM E 2180				
Openness factor	2%				
UV screen	Up to 99%				
Width	285 cm				
Weight/m ²	520 g ± 5% - ISO 2286 - 2				
Thickness	0,70 mm ± 5% - ISO 2286 - 3				
Colour Fasteness to light (scale of 8)	7/8 - ISO 105 B02 (white not graded)				
Mechanical resistance	Breaking	Tear	Folding		
Warp	> 200 daN/5 cm	≥ 10 daN	≥ 70 daN/5 cm		
Weft	> 170 daN/5 cm	≥ 8 daN	≥ 70 daN/5 cm		
	ISO 1421	EN 1875-3	ISO 1421		
Elongation (warp and weft)	< 5% - ISO 1421				
Packaging	Rolls of 33 lm				
Making up	Advice note on request				

This product's technical data are in conformity with this brochure as of the date of publication. MERMET SAS reserves the right to change the technical data; only those provided on the company's website www.sunscreen-mermet.com shall be deemed to be authentic. Where applicable, MERMET SAS also reserves the right to withdraw this product from sale should any of the technical properties or characteristics set out above prove to be inadequate or rendered impossible as a result of a change in regulations or in knowledge or understanding.

Reports available on request, please contact Mermet



0707

THERMAL AND OPTICAL FACTORS the European standard EN 14501


5500 MÉTAL	Thermal factors					Optical factors
OF 2 %	Fabric			Fabric + Glazing / gtot external blind		Tu
Colours(textil side factors)	Ts	Rs	As	C : gv = 0,59	D : gv = 0,32	Τv
0202 White	14	67	19	0,10 🔒	0,06	12
2020 Linen	12	55	33	0,08 🕚	0,05	9
0707 Pearl	10	38	52	0,07 4	0,05	8
0101 Grey	5	21	74	0,04 4	0,02 4	3

gv = 0,59: Solar factor of standard glazing (C), low-emission 4/16/4 double glazing filled with Argon (U value thermal transmittance = 1,2 W/m²K). gv = 0,32: Solar factor of standard glazing (D), reflecting low-emission 4/16/4 double glazing filled with Argon (U value thermal transmittance = 1,1 W/m²K).

Classification according to EN 14501 standard: 0 very little effect 1 little effect 2 moderate effect 3 yory good effect

Samples tested according to EN 14500 standard defining the measurements and calculation methods as specified in the standard EN 13363-2 "Solar protection devices combined with glazing calculation of solar and light transmittance - part 2: EN 13363-2 detailed method" and EN 410 "Glass in building - Determination of luminous and solar characteristics of glazing".

0707

















0202	
0202	
2020	
2020	
	and the second bar bar the second bar and the second bar bar the second bar bar bar bar
	art des versiones and des and des and des arts des versiones and des arts des versiones and des arts des versiones arts
0707	The set is and the set is a se
	a second the second
0101	
0101	

Colours may be slightly different from the actual ones

SERVICE

- Calculation of solar factor gtot (glazing + blind)
- Spectral values and thermal & optical factors available on request
- Specification sheet
- A4 samples and prototypes
- Training on fabrics functionality



MERMET U.K. Ryeford Hall , Ryeford , Ross-on-Wye HR9 7PU Phone 01989 - 750910 Fax 01989 750768 info@mermet.co.uk

This brochure must be read and interpreted in accordance with the General Terms & Conditions of Sale of MERMET SAS, with which it forms an indissoluble whole. The General Terms & Conditions of Sale that are current at any time are those contained on the MERMET SAS website at the following address: www.sunscreen-mermet.com.

MERMET