

### **OVERVIEW**

PU ADDASTONE ASPHALT RESIN is buff, dark grey, pink, dark green or grey two-part resin surface dressing, designed to bind natural aggregates. The finish achieved provides an attractive, safe, hard wearing and low maintenance surface.

## PREPARATION OF SURFACE

All bituminous surfaces to be treated with PU ADDASTONE ASPHALT RESIN must be sealed with Addacryl (refer to product information sheet) to prevent the resin from soaking in to the capillary pores.

Newly installed bituminous surfaces should be installed and compacted to current British Standard specifications. Examples of various suggested build ups are available on our website.

Existing bituminous surfaces must be of sound construction; any weakness could result in a bond failure or blistering. We strongly recommend that the client should take or, instruct, that core samples are taken to confirm base suitability.

#### SURFACES TO BE TREATED MUST BE DRY DO NOT APPLY IN WET CONDITIONS

#### HEALTH & SAFETY

Before using this product, please ensure you have been supplied and have read carefully the following:-

1. The hazard label (complying with CLP – European Regulation (EC) No. 1272/2008 on Classification, Labelling and Packaging of substances and mixtures) applied to the container.

2. Safety Data Sheet

Avoid prolonged contact with eyes and skin. For detailed information refer to relevant safety data sheet.

# CLEANING OF EQUIPMENT & SKIN

Tools, brushes etc... should be cleaned immediately after use in Addagrip Solvent Mixture. For cleaning of hands/skin, use a deep cleaning soap with water. Please note if a rash appears seek medical attention.

## MIXING & APPLICATION

PU ADDASTONE ASPHALT is supplied in units ready to use, comprising of Part 'A' (Resin) and Part 'B' (Hardener). First stir thoroughly contents in container 'A' to a homogenous consistency, then scrap contents of 'B' into container 'A' and mix thoroughly for several minutes using a low speed electric drill. Use protective gloves and goggles. Failure to mix thoroughly will result in poor or non cured material.

The temperature of the substrate must be 3 degrees above the dew point temperature of the atmosphere. See Addagrip Dew Point table for assistance. PU ADDASTONE ASPHALT should not be applied at temperatures below 5°C nor above 30°C. Relative humidity should not exceed 80%.

Apply the mixed PU ADDASTONE ASPHALT immediately by serrated squeegee onto the prepared surface. Particular attention should be given to areas around obstructions and protrusions making sure that all surfaces are covered.

PU ADDASTONE ASPHALT resin bonded surfaces must be thoroughly swept/vacuumed on completion. Further sweeping/vacuuming will also be required until the initial shedding of aggregate has been exhausted. Addastone contractors will generally carry out the first main sweep/vacuum only.

Note: The colour and textures of natural aggregates may vary from batch to batch. Small particles of iron may be present in natural aggregates that could lead to possible rust spotting/staining.

## PACKAGING & STORAGE

Packaged in 20kg and 1492kg units. Store containers in a clean dry area protected from direct sunlight and extreme heat and cold. Unopened containers can be stored for 3 months. Use oldest material first.





# **DISPOSAL CONSIDERTIONS**

Normally the Part A resin will be mixed in its own container with Part B. When this is done correctly the resultant material in the container is inert and the label must be defaced. The container and remnant may be disposed of as normal industrial waste. Any uncured material must be disposed as hazardous waste. Please consider the regional or national regulations regarding disposal.

# **TECHNICAL DATA**

| Product                 | Resin bonded polyurethane                                      |
|-------------------------|--|
| Density                 | 1.17g/cm <sup>3</sup>  |
| Colour                  | Buff, dark grey, pink, dark green or grey                      |
| Application Temperature | +10°C to 30°C  |
| Surface Temperature     | Must be 3°C above the dew point temperature.                   |
| Pot life at 20°C        | Approx. 30 minutes   |
| Initial cure at 20°C    | 5-8 hours  |
| Full Chemical Cure      | 7 days   |
| Packaging               | Supplied in 20kg and 1492kg units (2.80:1 mix ratio by weight) |
| Storage                 | 3 months in original unopened containers.                      |
|                         |  |

#### **COVERAGE RATES**

The minimum coverage rate for PU ADDASTONE ASPHALT RESIN is dependent on the chosen aggregate:

| Aggregate    | Resin Coverage      |
|--------------|---------------------|
| 0.5 – 1.5mm  | 1.0 – 1.2kg per sqm |
| 1.0 – 3.0mm  | 1.5 – 1.7kg per sqm |
| 2.0 – 4.0mm  | 1.9 – 2.1kg per sqm |
| 2.0 – 5.0mm  | 2.0 – 2.4kg per sqm |
| 6.0 -10.0 mm | 2.8 – 3.5kg per sqm |

Quantity of aggregate required to ensure complete blanket coverage:

| Aggregate    | Aggregate Coverage   |
|--------------|----------------------|
| 0.5 – 1.5mm  | 4.0 – 5.0kg per sqm  |
| 1.0 – 3.0mm  | 6.0 – 8.0kg per sqm  |
| 2.0 – 4.0mm  | 10.0 –12.0kg per sqm |
| 2.0 – 5.0mm  | 12.0 –14.0kg per sqm |
| 6.0 – 10.0mm | 18.0 –20.0kg per sqm |

For technical enquiries please contact your nearest representative:

UK: ADDAGRIP Tel: +44 (0)1825 761 333 E-mail: <u>sales@addagrip.co.uk</u> Web: <u>www.addagrip.co.uk</u> / <u>www.terraco.com</u>