

**FILL AND SKIM
REINFORCED
WITH FIBERS**

FIBAREX®

FILL, REPAIR AND FACE FILLER



- ▶ **EXCEPTIONAL ADHERENCE**
- ▶ **WILL NOT FLASH OR GRIN**
- ▶ **PAINT IN 24 H**
- ▶ **MOISTURE VAPOUR PERMEABLE**
- ▶ **NO STABILISING SOLUTION OR PVA REQUIRED***
- ▶ **EASY TO SAND**

PURPOSE

Repair powder filler for filling and face filling with added fiber, for exterior use, manual application.

SUBSTRATES

FIBAREX® applies on either new or renovated substrates, either unpainted or painted:

- Gypsum plaster
- Old painted surfaces
- Cement, concrete, breeze blocks, bricks, stones
- Glass tiles, earthenware tiles

OVERCOATING

FIBAREX® can be overcoated by all types of paints: mineral paints, waterproofing coatings and **TOUPRET** exterior fillers. Do not cover straight over with polyurethane or solvent-based epoxy paints.

Physical and technical FEATURES

FIBAREX® is a powder filler, for exterior use, made with cement, selected mineral extracts, binders and fibres.

- Characterization (NFT 36-005): Family IV class 4c
- Codification (EN 16-566): $G_3S_2V_1W_1A_0C_0R_0$
- Mixing rate: 40% water (hence 0,4 l water for 1 kg powder)
- Application thickness: limitless
- Consumption: 1.1 kg/m²/mm
- Working time: 40 minutes
- Second coat: once the filler is dry
- Overcoat: 24 H average time (once completely dry)
- Colour: white
- Shore hardness: 85
- pH: 11 right after mixing – 9 after 24 H
- Adhesion filler/substrate (EN 16-566): > 0,8 MPa

USE AND STORAGE CONDITIONS

- Application tools : coating knife or with trowel or blade
- Tools cleaning: the product residues are to be rubbed off when dry. Water cleaning is unnecessary.
- Preservation: product guaranteed 6 months, from the original purchase invoice date as evidence, in its original sealed packaging and stored away from humidity.

*On hard, cohesive, clean, sound and dry substrates.

PACKAGING

- Box of 2 kg.
- Bag in bag 5x1 kg.

RECOMMENDATIONS and care for use

- Do not apply on polystyrene, nor on damp substrates.
- Do not apply under a temperature < 5 °C and > 35 °C nor under an hygrometry rate over 80%..
- The setting of the paste depends on its temperature: a high temperature will make it set quicker whereas a low temperature will make it set slower.
- When the product starts to harden, it is recommended to no longer mix, nor to reuse.

SUBSTRATES PREPARATION

- Substrates to be prepared as per the current trade practices.
- Substrates must be hard, cohesive, clean, sound and dry.

NORMATIVE DOCUMENTS to be referred to

- EN 16-566: Coating fillers for interior works and/or exterior.
- NFT 36-005: Characterization of paint products.
- French DTU 59.1 (NFP 74-201): Building paint works.
- French DTU 42.1 (NFP 84-404): façades renovation with polymer-based waterproofing coatings.

HEALTH AND SAFETY

- Contains cement – please read the care for use guidelines on the packaging or on the MSDS before handling.
- Safety data sheets available on www.toupret.co.uk

The data sheet information, especially the guidelines relevant to the application and final use of **FIBAREX®** are provided in good faith and result from the knowledge of the products and experience of **TOUPRET** company.

The product is required to be used as per the trade practices rules book and in reference to our recommendations.

The information provided is relevant to applications processed under a temperature of 20°C, a hygrometry rate of 50 % and on normal-absorbent substrates.

The times mentioned are only indicative and depend on the substrate, the coat thickness, and the ambient conditions.