

# [3 in 1]

## MULTIPURPOSE FILLER

### FILL, JOINT AND FACE FILLER



- ▶ **ADHERES TO PAINTED SURFACES**
- ▶ **EXCELLENT COVERAGE RATE**
- ▶ **WILL NOT FLASH OR GRIN**
- ▶ **TAPING AND JOINTING PLASTER BOARDS**
- ▶ **EASY TO SAND**

#### PURPOSE

Adhesive and filler, in powder form, for interior use, manual application.

#### SUBSTRATES

**MULTIPURPOSE FILLER** applies on painted or unpainted substrates:

- Gypsum plaster, plasterboard,
- Plaster tiles,
- Old painted surfaces,
- Any filler of **TOUPRET** range,
- Cement, concrete, cellular concrete, breeze blocks, bricks, stones

#### OVERCOATING

**MULTIPURPOSE FILLER** can be overcoated by any fillers of **TOUPRET** range, any conventional paints and wall coverings.

#### Physical and technical FEATURES

**MULTIPURPOSE FILLER:** adhesive and filler, in powder form made of quarry extracts and cellulosic binder.

- Characterization (NFT 36-005): Family III class 3
- Codification (NFT 30-608):  $G_3E_3S_3V_0W_0A_0C_0$
- Mixing rate: for filling purpose: 38% water  
(hence 0.38 litre water for 1 kg powder)  
for adhesive/levelling purpose: 42 % water  
(hence 0.42 litre water for 1 kg powder)
- Application thickness: Filling: no thickness limit  
Levelling coat: up to 5 mm
- Consumption: Adhesive purpose: 2 to 3 kg/m<sup>2</sup>  
Coating purpose: 1,1 kg/m<sup>2</sup>/mm
- Second coat: 45 min
- Overcoating: 24h to 48h average time (after complete drying)
- Colour: white
- Shore hardness: 75
- Adhesion filler/substrate (NFT 30-608) : > 0,5 MPa

#### USE AND STORAGE CONDITIONS

- Application tools: coating blade or trowel
- Tools cleaning: the product residues are to be rubbed off when dry. Water cleaning is unnecessary.
- Preservation: product guaranteed 12 months, from the original purchase invoice date as evidence, in its original sealed packaging and stored away from humidity.

#### PACKAGING

- Box of 2 kg
- Bags of 5 and 10 kg

#### RECOMMENDATIONS and care for use

- Do not apply under a temperature below 8 °C and above 35 °C nor under a hygrometry rate over 70 %
- Do not apply on warm/overheated surfaces
- Do not apply on damp substrates.
- Prepare the mixing in water at room temperature
- Do not apply **MULTIPURPOSE FILLER** on polystyrene, nor on wall paper, nor on exterior substrates.

#### SUBSTRATES PREPARATION

- Substrates to be prepared as per the current trade practices.
- Substrates must be hard, cohesive, clean, sound and dry.

#### NORMATIVE DOCUMENTS to be referred to

- NFT 30-608: Coating fillers for interior works and/or exterior.
- NFT 36-005: Characterization of paint products.
- DTU 59.1 (NFP 74-201): travaux de peinture des bâtiments.
- DTU 59.4 (NFP 74-204): Mise en œuvre des papiers peints et des revêtements muraux.
- French DTU 25.31 (NF P72-202-2): Vertical works which do not require a gypsum plaster based coat. Setting up of partition or plaster tiles.
- French DTU 25.41 (NF P 72-203-1): Plasterboards works.

#### HEALTH AND SAFETY

- No danger tag.
- FDS disponible sur [quickfds.com](http://quickfds.com) ou [toupret.com](http://toupret.com).

The data sheet information, especially the guidelines relevant to the application and final use of **MULTIPURPOSE FILLER** are provided in good faith and result from the knowledge of the products and experience of **TOUPRET** company.

The product is required to be used as per the trade practices rules book and in reference to our recommendations.

The information provided is relevant to applications processed under a temperature of 20°C, a hygrometry rate of 50 % and on normal-absorbent substrates.

The times mentioned are only indicative and depend on the substrate, the coat thickness, and the ambient conditions.