

AIRSPRAY J

VERY FINE, READY TO USE FINISHING TOP-COAT SPRAY PLASTER

SPRAY OR MANUAL JOINT FILLER

- ◆ SPRAYABLE
- ◆ VERY FINE
- ◆ CERTIFIED FOR JOINTING
- ◆ EXCELLENT FINISHING COAT
- ◆ EASY TO TROWEL AND SAND



PURPOSE

Ready to use dry wall joint compound to be used in association with a joint tape, interior use, manual application. Can also be used as finish surface filler.

SUBSTRATES

Airspray® J can be applied on any type of plasterboards with thin edges with or without insulating parts and plaster carton boards.

OVERCOATING

Airspray® J can be coated with any type of primer or a surface filler.

Physical and technical FEATURES

- Airspray® J: filler in ready mixed form for interior use, made of mineral components and synthetic resin.
- Characterization (NFT 36-005): Family III - Class 2.
- Codification (EN 16566): $G_3S_1V_0W_0A_0C_0R_0$.
- Mixing rate: ready to use.
- Application thickness: up to 5 mm.
- Coverage: Approx. 350g/ml - 1.7 kg/m²/mm.
- Setting time: second coat as soon as the filler is hard and dry to the touch.
- Overcoating: can be painted in 24 to 48 hours average time (after completely dry).
- Color: white
- Adhesion: filler/substrate (EN 16566): > 0.5 Mpa.

USE AND STORAGE CONDITIONS

- Application tools: any airless machine with a minimum flow of 5 L/min.
- For optimum use, we recommend the following nozzles: 3.31 to 6.35.

- Smooth or surfacing blade.
- Tool cleaning: with water.
- Preservation: product guaranteed 12 months.

Stored away from sunlight and frost.

If found to be faulty within the guarantee period, we will arrange a replacement on proof of purchase.

PACKAGING

- Bucket: 25kg.

RECOMMENDATIONS and care for use

The times mentioned are indicative and depend on the substrate, coat thickness, and the ambient conditions.

Do not apply at a temperature below 8°C or above 35°C nor at a relative humidity over 70%.

Do not apply on overheated surfaces or damp substrates.

Do not apply on polystyrene, nor on wall paper, nor on exterior substrates.

SUBSTRATES PREPARATION

Substrates to be prepared as per the current trade practices.

Substrates must be hard, cohesive, clean, sound and dry.

NORMATIVE DOCUMENTS to be referred to

- EN 16566: Coating Fillers for interior and/or exterior works.
- NFT 36-005: Characterization of paint products.
- DTU 59.1 (NFP 74-201): Building paint works.
- DTU 25.41 (NFP 72-203-1) Building works - Gypsum plaster-board works - Gypsum wallboards.
- NF Environment – Paint fillers (NF446).
- BS EN 13963 : 2014 - Jointing materials for gypsum boards.

HEALTH AND SAFETY

It is recommended to wear gloves and glasses while applying Airspray® J.

Dispose of unused product and packaging responsibly at your local waste collection centre.

Preservatives: Contains 1,2-benzisothiazolin-3-one; C(M)IT / MIT (3:1); MBIT. May produce an allergic reaction. Safety data sheet available at www.toupret.co.uk

The data sheet information, especially the guidelines relevant to the application and final use of the product are provided in good faith and result from TOUPRET's experience and knowledge of the products. The product should be used as per the trade practices rules book and in reference to our recommendations. The information provided is relevant to applications processed at a temperature of 20°C, a relative humidity of 50% and on average absorbency substrates. The times mentioned are only indicative and depend on the substrate, the coat thickness, and the ambient conditions.



* Information on the emission level of volatile substances into indoor air, presenting a risk of toxicity by inhalation, on a scale from A+ (very low emissions) to C (high emissions).