

Protective & Marine Coatings

PRODUCT DATA SHEET

MACROPOXY® 646 AEROSOL

EPOXY PRIMER FINISH

Revised: 09/2019 Issue 1

PRODUCT DESCRIPTION

MACROPOXY 646 AEROSOL is a two component fast drying, surface tolerant, polyamide epoxy that has been packaged in a single aerosol to protect steel in an industrial environment. The packaging makes it the ideal product for use in maintenance situations due to its ease of application in a range of environments.

INTENDED USES

Recommended for small repairs in refineries, offshore platforms, chemical plants, tank externals, power plants and bridge and highways. It can be applied to manually prepared surfaces providing protection to range of structures and assets.

PRODUCT DATA

Finish: Semi-Gloss

Color: Mid-Grey, Green, Yellow and Magnolia

Volume Solids: 53% 71% Weight Solids:

VOC: 390.25 a/l

Typical Thickness:

Recommended Spreading Rate per coat:

Minimum Maximum

Dry mils (microns) 3.0 (75) 4.0 (100)

Theoretical coverage per can is 5.0 sq ft (0.46 m²) @ 3 mils / 75 microns dft.

Shelf Life: 12 months minimum at 77°F (25°C). Subject to

inspection thereafter. Store in dry, shaded conditions away from sources of heat or ignition.

Packaging: Macropoxy 646 can be ordered in 6 aerosols

per box. Each aerosol contains 10.9 fl. oz. (322 mL) of product.

Average Drying Times @ 7.0 mils (175 microns) wet:

35°F (2°C) 77°F (25°C) 100°F (38°C) 50% RH 50% RH 50% RH Touch: 5 hours 2 hours 1.5 hours Handle: 48 hours 8 hours 4.5 hours Recoat (minimum): 48 hours 8 hours 4.5 hours Pot Life: 10 hours 4 hours 2 hours

Drying time is temperature, humidity, and film thickness dependent.

SURFACE PREPARATION

Surface must be clean, dry, and in sound condition. Remove all oil, dust, grease, dirt, loose rust, and other foreign material to ensure adequate adhesion.

Minimum recommended surface preparation:

Iron & Steel: Atmospheric: SSPC-SP2/3 / ISO8501-1:2007 St 2/St 3



Protective & Marine Coatings PRODUCT DATA SHEET

MACROPOXY® 646 AEROSOL

APPLICATION

Temperature (air, surface, & material):

Relative humidity:

Ensure the correct PPE is worn before the following process is started:

40°F (4.5°C) minimum, 120°F (49°C)

APPLICATION CONDITIONS

Step 1 – Shake the aerosol until agitator ball is free & place on a flat surface

maximum At least 5°F (2.8°C) above dew point

Step 2 – Remove cap and insert the metal ring provided

85% maximum

ADDITIONAL NOTES

Step 3 - Pull fully out and twist 360° to release the activator

This product is intended for use only by professional applicators in industrial situations utilising the advice given on this guidance sheet, the material safety data sheet of the product and the information on the aerosol container.

Step 4 – Shake the aerosol can for at least two minutes after agitator ball is free

All work involving the application and use of this aerosol based product should be performed in compliance with all relevant national or corporate Health & Safety & Environmental standards and regulations.

- Step 5 Apply in cross coats keeping the aerosol can 250mm from the surface
 Step 6 After use turn the aerosol can upside down to empty
- Spray can should be held vertical to the surface. Press down on the tip around 10" (can vary depending on conditions) and maintain

an even distance from the surface throughout the application.

Step 1	Step 2	Step 3	Step 4	Step 5	Step 6

WARRANTY

The Sherwin-Williams Company warrants our products to be free of manufacturing defects in accord with applicable Sherwin-Williams quality control procedures. Liability for products proven defective, if any, is limited to replacement of the defective product or the refund of the purchase price paid for the defective product as determined by Sherwin-Williams. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY SHERWIN-WILLIAMS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

HEALTH AND SAFETY

Refer to the SDS sheet before use.

Published technical data and instructions are subject to change without notice. Contact your Sherwin-Williams representative for additional technical data and instructions.

DISCLAIMER

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Sheet.